

---

<b>Product name</b>	:	<b>Carat Chrome Effect</b>		
<b>Colour</b>	:	<b>Chrome Silver</b>	<b>Chrome Gold</b>	<b>Chrome Copper</b>
<b>Article number</b>	:	<b>08201</b>	<b>08200</b>	<b>08202</b>
<b>Supplier / Producer</b>	:	<b>MOTIP DUPLI B.V.</b>		
		<b>Wolframweg 2</b>		
		<b>NL-8471 XC WOLVEGA</b>		
		<b>Telephone number</b>	<b>+31 561 – 69 44 00</b>	
		<b>Telefax number</b>	<b>+31 561 – 69 44 31</b>	

---

### Product description

High quality, fast-drying, decorative lacquer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic.

### Productkenmerken

Excellent coverage  
Metallic gloss  
Not rub resistant  
Not resistant to weather influences  
Excellent adhesion



### Physical and Chemical Characteristics

Contents	:	400 ml
Base	:	Acrylic resin
VOC-content	:	Approximately 84% w/w
Solid content	:	Approximately 16% w/w
Gloss	:	Metallic
Coverage	:	1,25 to 1,75 m <sup>2</sup>
Dust dry	:	After 5 to 10 minutes
Hardened	:	After 24 hours
Heat resistant	:	To 110°C

### Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

#### Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of Carat primer suitable for the surface. After drying, sand the base layer (grain 600).

#### Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

**Not re-sprayable with clear varnish.**

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**